



Anarchy™



Physical Properties

Color:	Anarchy™ Golden Wheat/Plum/Ultra Violet
Coverstock:	R3X™ Pearl Reactive
Weight Block:	Origin™
Ball Finish:	1500-grit Polished
Logos:	Anarchy, CG, Bolt (PSA), Storm
Durometer:	73-75
Flare Potential:	6" Plus (High)
Fragrance:	Aromatherapy Focus
Available Weights:	12-16 lbs.
SKU:	TAN

Ball Weight	Radius of Gyration	Diff	Intermediate Diff
16#	2.49	.054	.015
15#	2.48	.057	.017
14#	2.52	.045	.012



Resurfacing Method:

Follow the steps below to take the ball back to "out of the box" condition. Items needed: 500-grit Abralon, a Grey Scotch-Brite™ Pad, Storm® Step Two™ Polish, a ball spinner and water. All sanding should be done on four sides of the ball. Side one - center of grip up, flip the ball 180 degrees for side two, turn 90 degrees for side three, and flip another 180 degrees for side four.

1. Using the 500-grit Abralon pad, sand the ball for 15 seconds on each side.
2. Using the Grey Scotch-Brite pad, sand the ball for 40 seconds on each side.
3. Using the Storm Step Two, polish the ball on two sides for 15 seconds on each side.

Suggested Maintenance:

Storm suggests using Reacta Shine™ Reactive Ball Cleaner/Polish to clean your bowling ball after every bowling session.

To touch up the surface, skip step #1 and use step #2 and #3 only. Storm suggests using step #2 and #3 from above, every 20-30 games. Use all steps every 50-60 games. This will increase longevity and create a more consistent reaction for your new Storm bowling ball.

